

Product Data Sheet

Code Number : PF610-R

NO	Item	Specification	Standard
1	Appearance	Bright and shiny surface finishes	
2	Alloy	Sn/Ag3.0/Cu0.5/Ni0.06/Ge0.01	JIS-Z-3282 A CLASS
3	Melting Point	217~219°C	DSC
4	Flux Content	3.0 ±0.5 %	JIS-Z-3283
5	Halide Content	Under 0.1%	JIS-Z-3283
6	Gravity	7.4	
7	Spread ability	> 75%	JIS-Z-3197
8	Packaging	200g, 250g, 500g, 1kg/Rool	JIS-Z-3283
9	Diameters Tolerances	0.3~0.6± 0.05 mm , 0.8~1.6 ± 0.1 mm	JIS-Z-3283
10	Flux Type	ROL1	J-STD-004
11	Features	Excellent solder joint reliability. Superior joint strength. Excellent thermal & Mechanical fatigue resistance. Low cleaning required after solder joint	
12	Purpose	For use in applications requiring good activation.	

Physical Properties & Reliability Data

No	Test Item	Test Result	Test Method
1	Silver Chromate Test	PASS	IPC-TM-650, 2.6.33
2	Copper Mirror Test	PASS	IPC-TM-650, 2.6.32
3	Copper plate Corrosion	PASS	JIS-Z-3197, 6.6.1
4	S.I.R Test	1×10 ⁹ up	IPC-TM-650, 2.6.3.3
5	Electro migration Test	1×10 ⁹ up	IPC-TM-650, 2.6.14.1

ALLOY COMPOSITION

(Sn)	(Ag)	(Cu)	(Ni)	(Ge)	(Zn)	(Al)	(Sb)	(Fe)	(As)	(Bi)	(Cd)	(Pb)
REM.	2.7~ 3.3	0.3~ 0.7	0.04~ 0.08	0.005~ 0.02	0.002 MAX	0.002 MAX	0.12 MAX	0.02 MAX	0.03 MAX	0.10 MAX	0.002 MAX	0.05 MAX

Patent No. : Japanese Patent No. 3296289 ◦ U.S Patent No. 6179935B1.

Headquarter and Factory:

SHENMAO TECHNOLOGY INC.

Shenmao Micro Material Institute

No.12-1 Gongye 2nd Rd., Guanyin industrial area,
Taoyuan County 328 Taiwan, R.O.C.

Tel: 03-416-0177 Fax: 03-416-0133

Mail: sales@shenmao.com

SHEN MAO SOLDER (M) SDN. BHD.

NO.7 LORONG JELAWAT LAPAN, KAWASAN PERUSAHAAN
SEBERANG JAYA, SEBERANG JAYA, S.P.T. 13700,PERAI
PULAU PENANG, MALAYSIA

TEL : (60-4)3995259 、 3995349 FAX : (60-4)399525

SHEN MAO SOLDERING TIN CO., LTD

The 2nd Ind. Area Jiumen Village Hu Men
Town Dong Guan City , China

Tel: (86-769)-550-8193 Fax: (86-769)-550-4789

SHEN MAO INDUSTRY (HK) LTD

RM.1313-1314, 13/FL., Fo Tan Industrial Centre, 26- 28 Au Pui
Wan Street, Fo Tan, N.T., Hong Kong

Tel: (852)2697-3366 Fax: (852)2694-7533

SHENMAO SOLDER MATERIAL(SUZHOU)CO.,LTD

No.1447,Chung San North Road, Wu Chiang economic Development Area, Sung Lin Town, Wu Chiang City, Suzhou
Province, P.R.C Tel: (86-512)6345-1092 Fax: (86-512)6345-1095

www.shenmao.com